



# Pro-Seal 2000 Wet Look Lacquer

## A ULTRA HI-GLOSS LACQUER BASED SEALER



### COVERAGE:

1 gallon (3.8 Liters) covers approximately 250 sq. ft. to 400 sq.ft.

### PACKAGING:

Available in 1 gallon jugs, 5 gallon pails and 55 gallon drums.

### STORAGE:

1. Store in a cool, dry location.
2. Store out of direct sunlight.
3. Protect pails and jugs from weather and other damage.
4. Store at a temperature between 40°F (4°C) and 90°F (32°C).

### SHELF LIFE:

2 years

### COLOR:

Clear Hi Gloss

Visit us online:

[ClassicCoatingsSystems.com](http://ClassicCoatingsSystems.com)

See Our Website Gallery to  
Get Inspired and  
View How-to Videos & SDS

### DESCRIPTION

Classic Pro-Seal 2000 is a high gloss, low VOC, single component, high solids, solvent (acetone) base sealer that is designed to be used over our acid stain, water based stains, polymer modified cementitious toppings, concrete, waterborne colorants, masonry, stone, pavers, and brick. It may be used for exterior applications in a wide range of climates. Pro-Seal 2000 Wet Look has excellent UV stability and will not yellow. Pro-Seal 2000 is formulated primarily as a clear seal for applications over concrete restoration products and pool deck coatings where a low maintenance, easily cleanable surface is desired. May also be applied to Spanish tile, stucco, overlays, and natural stone, provided the surface is properly prepared. Pro-Seal 2000 Wet Look cleans up easily with soap and water. After two applications, wait 48 hours before parking a vehicle. Available in 1g jugs, 5g pails, and 55g drums. **Caution: Surface is slippery when wet. New concrete must cure for 28 days.**

### ADVANTAGES

Resists water penetration & waterproof
Low VOC <100 g/l and enhances color
Cross-Link & High UV stability
Excellent hot tire pick-up
Excellent adhesion and durability
Low cost, easy installation and low maintenance
Easy to clean with soap and water

### LIMITATIONS

May reflect working cracks in substrate
Recommended application temperature should be between 55° F and 85° F
Must be installed over a clean dry surface
Not freeze thaw
Not for use under water
Surface must not contain moisture and efflorescence

### TYPICAL USAGE

- Pool Decks (Slippery when wet)
- Driveways
- Walkways
- Over stained concrete
- Restoration projects
- Architectural toppings
- Concrete floors
- Block walls
- Patios
- Masonry
- Spanish Tile
- Stucco
- Natural Stone

REVISED: March 2020

Classic Coatings Systems • 255 Citation Circle, Corona, CA 92878

© 2015 Classic Coatings Systems Inc. All rights reserved.



# Pro-Seal 2000 Wet Look Lacquer

## A ULTRA HI-GLOSS LACQUER BASED SEALER

### PREPARATION

- ✓ **READ SDS BEFORE HANDLING & APPLICATION**
- ✓ Highly recommended to test a small inconspicuous area first.
- ✓ **TURN OFF SPRINKLERS FOR TWO DAYS PRIOR TO AND AFTER.**
- ✓ Always protect neighboring surfaces including wood, carpet, metal, landscaping and other non-masonry surfaces.
- ✓ **Caution: Surface is slippery when wet.**
- ✓ New concrete must cure for 28 days before sealer is apply.

### INSTALLATION

1. Prepare surface by carefully and thoroughly removing all traces of any foreign matter.
2. Apply first coat of Pro-Seal 2000 Sealer by brush, roller or sprayer.
3. Repeat step (2) for the second coat.
4. A third application may be required in high traffic areas.

Cure Time at 75°F: Dry to touch in 30-60 minutes, re-coat after 1-2 hours, light foot traffic after 6 hours and full cure in 3 days.

NOTE: System thickness 3-4 wet mils. per coat.  
Standard application is two coats.

Classic Pro-Seal 2000, when used with a small percentage of Classic's Series Pigment Concentrate, can also provide a carrier for stain washing and faux finish techniques.

### PHYSICAL CHARACTERISTICS & TECHNICAL DATA

- Coverage per liquid gallon 250-400 sq ft per gallon
- Abrasion - Good
- VOC < 100 g/l
- Degree of Gloss – Hi-Gloss
- Solids content by volume: 23+ %

It is HIGHLY recommended that on-site samples and mock-ups be made by the applicator. Representative test sections must be produced for the owner's approval in writing and to ensure that applicators are familiar with the product and installation procedures.

Disclaimer: The information and recommendations contained herein are based upon data believed to be correct; however, no guarantee or warranty of any kind, express or implied is made with respect to the accuracy of the information contained herein. We accept no responsibility and disclaim all liability for any harmful effects, which may be caused by exposure to our products. Customers and users of this product must comply with all applicable health and safety laws, regulations and orders.

### PRODUCT AVAILABILITY & TECHNICAL ASSISTANCE

Technical assistance and information is available by calling:

(951) 279-2600

[www.classiccoatingsystems.com](http://www.classiccoatingsystems.com)

#### HANDLING PRECAUTIONS:

Use only with adequate ventilation. An appropriate cartridge type respirator must be used during application in confined areas. Avoid contact with skin. Protective gloves, eyewear and clothing are recommended.

#### PROP 65 WARNING:

Classic Coatings, as a blender of processed material in the State of California, is required by Proposition 65 to warn that one or more of the components contained in the product contain chemicals known to the State of California to cause cancer, birth defects or other reproductive harm. The State of California (Proposition 65) requires this warning in the absence of definitive testing to prove that the defined risks do not exist. We believe this product complies with all other applicable state and federal laws and regulations governing manufacturing, distribution and intended use. User is solely responsible for the legal disposal of this container and/or its contents.

#### WARRANTY:

Classic Coatings products are warranted for one year after date of purchase. Please refer to the Limited Material warranty for additional clarification. NOTICE TO BUYER: DISCLAIMER OF WARRANTIES AND LIMITATIONS ON OUR LIABILITY. We warrant that our products are manufactured to strict quality assurance specifications and that the information supplied by us is accurate to the best of our knowledge. Such information supplied about our products is not a representation or a warranty. It is supplied on the condition that you shall make your own tests to determine the suitability of our product for your particular purpose. Any use or application other than recommended herein is the sole responsibility of the user. Listed physical properties are typical and should not be construed as specifications. NO WARRANTY IS MADE, EXPRESSED OR IMPLIED, REGARDING SUCH OTHER INFORMATION, THE DATA ON WHICH IT IS BASED, OR THE RESULTS YOU WILL OBTAIN FROM ITS USE. NO WARRANTY IS MADE, EXPRESSED OR IMPLIED, THAT OUR PRODUCT SHALL BE MERCHANTABLE OR THAT OUR PRODUCT SHALL BE FIT FOR ANY PARTICULAR PURPOSE. NO WARRANTY IS MADE

THAT THE USE OF SUCH INFORMATION OR OUR PRODUCT WILL NOT INFRINGE UPON ANY PATENT. We shall have no liability for incidental or consequential damages, direct or indirect. Our liability is limited to the net selling price of our product or the replacement of our product, at our option. Acceptance of delivery of our product means that you have accepted the terms of this warranty whether or not purchase orders or other documents state terms that vary from this warranty. No representative is authorized to make any representation or warranty or assume any other liability on our behalf with any sale of our products. Our products contain chemicals that may CAUSE SERIOUS PHYSICAL INJURY. BEFORE USING, READ THE MATERIAL SAFETY DATA SHEET & FOLLOW ALL PRECAUTIONS TO PREVENT BODILY HARM.